DURLON[®]7900/7925/7950

Aramid with NBR Rubber Binder Compressed Asbestos Free Gasket Material ASTM F104: F712120-A9B3E22K5L151M5

Colour	7900 - Off White 7925 - Lt. Green 7950 - Blue	
Fiber System	Aramid/Inorganic	
Binder	NBR	
Temperature Min Max Continuous, Max	-73°C (-100°F) 371°C (700°F) 260°C (500°F)	
Pressure, max, bar (psi)	83 (1,200)	
Density, g/cc (lbs/ft3)	<mark>1.7</mark> (106)	
Compressibility, % ASTM F36	7-17	
Recovery, % ASTM F36	40	
Creep Relaxation, % ASTM F38	20	
Tensile Strength, across grain ASTM F152, MPa (psi)	11 (1,600)	
Fluid Resistance <mark>,</mark> ASTM F146 IRM 903 Oil 5hrs at 300°F		
Thickness Increase, % Weight Increase, % ASTM Fuel B 5hrs at 70°F	0-15 15	
Thickness Increase, % Weight Increase, %	0-10 12	
Sealability, cc/min ASTM 2378 (Nitrogen) Sealability, ml/hr	0.05	
ASTM F37 (Fuel A) ASTM F37 (Nitrogen)	0.03 0.5	
Flexibility ASTM F147	10x	

Note: ASTM properties are based on 1/16" sheet thickness, except ASTM F38 which is based on 1/32" sheet thickness. This is a general guide only and should not be the sole means of accepting or rejecting this material. The data listed here falls within the normal range of product properties, but should not be used to establish specifications limits nor used alone as the basis of design. For applications above Class 300, contact our trachesical description.



Download iGasket[®] on your

smartphone today!




Triangle Fluid Controls Ltd.[®] Belleville, ON CANADA info@trianglefluid.com

f - 613.968.1099 tf - 866.537.1133

t - 613.968.1100





Warning: Durlon® gasket materials should never be recommended when both temperature and pressure are at the maximum listed. Properties and applications stated are typical. No applications should be undertaken by anyone without independent study and evaluation for suitability. Never more than one gasket in one flange joint and never reuse a gasket. Improper use or gasket selection could cause property damage and/or serious injury. Data reported is a compilation of field testing, field service reports and/or in-house testing. While the utmost care has gone into publishing the information contained herein, we assume no responsibility for errors. Specifications and information contained in this flyer are subject to change without notice. This edition cancel and obsoletes all previous editions.

Gasket Factors		
	<u>1/16"</u>	<u>1/8"</u>
m	3.0	3.2
Y, psi (MPa)	3,347 (23.1)	3,385 (23.3)
G _b , psi (MPa)	497 (3.4)	486 (3.4)
а	0.226	0.276
G _s , psi (MPa)	3 (0.02)	0.4 (0.003)



Anti-Stick Properties:

Much effort has gone into improving the anti-stick release agents of all compressed Durlon[®] products. All Durlon[®] compressed gasket materials have passed the MIL-G-24696B Navy Adhesion Test (366°F/48hrs).

Durlon 7900 REV 2016-7

info@trianglefluid.com www.trianglefluid.com