

## HT1000<sup>®</sup> Paste

High Temperature Sealing Compound

HT1000<sup>®</sup> is a registered trademark of Triangle Fluid Controls Ltd.



Durlon<sup>®</sup> HT1000<sup>®</sup> Paste is a sealing compound designed to be used in conjunction with our HT1000<sup>®</sup> sheet material specifically for large dovetail gaskets. The paste allows end users to create larger diameter gaskets using cost effective dovetail gasket segments. The HT1000<sup>®</sup> Paste allows end users to eliminate possible leak paths of traditional dovetail gaskets, while providing end users the one piece gasket construction and lower leakage rates similar to one-piece gasket.

Available in 170 g and 90 g containers.

### SHELF LIFE:

6 months in unopened container from the date it was packaged.

### INSTRUCTIONS:

1. Make sure gasket segments are aligned and laying flat pre-assembled. Ensure that both the gasket and flange are free of debris, oils, and grease.
2. Open container of HT1000<sup>®</sup> Paste and apply a thin, even layer to the dovetail portion of the gasket, using a disposable brush or putty knife, smoothing out any uneven portions.
3. Assemble flange and tighten bolts according to gasket manufacturer's recommendations (torque, bolt-up method, etc.).
4. HT1000<sup>®</sup> Paste will begin to cure in service (Please see applicable curing time chart to left).

### Physical Properties

Temp.: Min Max	260°C (500°F) 1,000°C (1,832°F)
Curing Temperature	Required Cure Time
149°C (300°F)	4 Hrs
204°C (400°F)	3 Hrs
260°C (500°F)	2 Hrs
316°C (600°F)	1 Hr
371°C (700°F) or Higher	<1 Hr

**Note:** In high pressure gasket sealing applications or if ambient pressure testing is being performed, it is recommended that the HT1000<sup>®</sup> Paste be pre-cured with a heat source such as a heat gun or oven if available prior to putting the gasket into pressurized service.

**Warning:** Durlon<sup>®</sup> gasket materials should never be recommended when both temperature and pressure are at the maximum listed. Properties and applications stated are typical. No applications should be undertaken by anyone without independent study and evaluation for suitability. Never use more than one gasket in one flange joint and never reuse a gasket. Improper use or gasket selection could cause property damage and/or serious injury. Data reported is a compilation of field testing, field service reports and/or in-house testing. While the utmost care has gone into publishing the information contained herein, we assume no responsibility for errors. Specifications and information contained within are subject to change without notice. This edition cancels and obsoletes all previous editions.